

## ON THE MODELING OF LOAD INTERACTION EFFECTS ON CURVED FATIGUE CRACKS

A.C.O. Miranda<sup>1</sup>, M.A. Meggiolaro<sup>2</sup>, J.T.P. Castro<sup>2</sup>, L.F. Martha<sup>3</sup>

<sup>1</sup> Tecgraf - Computer Graphics Technology Group, <sup>2</sup>Department of Mechanical Engineering, <sup>3</sup>Department of Civil Engineering, Pontifical Catholic University of Rio de Janeiro  
Rua Marquês de São Vicente 225 – Gávea, Rio de Janeiro, RJ, 22453-900, Brazil

### ABSTRACT

A hybrid global-local methodology to predict fatigue crack propagation in 2D structures is extended to model crack retardation effects induced by variable-amplitude (VA) loading histories. First, finite element (FE) models are used at each propagation step to calculate the generally curved fatigue crack path. However, the FE approach alone is not computationally efficient to predict crack growth rate, because it would require time-consuming remeshing of the entire structure after each event in VA loading. Therefore, the crack path and their mixed-mode stress intensity factors are FE calculated under constant-amplitude (CA) loading using fixed crack increments, requiring only relatively few remeshing steps. An analytical expression is then fitted to the calculated  $K_I$  values, which is used in a local-approach fatigue design program to predict crack propagation lives under VA loading, considering load interaction effects such as crack retardation or arrest after overloads. This methodology is experimentally validated by fatigue crack growth tests on compact tension C(T) specimens, modified with holes positioned to attract or to deflect the fatigue cracks. Experiments under VA loading are also performed on C(T) specimens without holes. Several crack retardation models are calibrated based on straight-crack data. These models are then used to successfully predict the curved crack growth behavior under VA loading of the hole-modified specimens.

### KEYWORDS

Curved crack path, Retardation models, Finite elements, Mixed-mode loading

### INTRODUCTION

Fatigue life prediction of cracked two-dimensional (2D) structural components requires the calculation of the generally curved crack path, the associated stress intensity factors (SIF)  $K_I$  and  $K_{II}$ , and the crack propagation rate at each load step [1]. A finite element (FE) global discretization of the component, using specialized crack tip elements to predict the crack path and to calculate its associated SIF, is a standard practice. However, this global calculation method is not computationally efficient under variable amplitude (VA) loading to predict fatigue lives, because it requires time-consuming remeshing procedures and FE recalculations after each loading event.

On the other hand, the so-called local approach, based on the direct integration of the crack propagation equation, can be efficiently used to calculate the crack increment at each load cycle, considering crack

retardation effects if necessary. However, this approach requires the stress intensity expression  $K_I$  for the crack, which is not available for most real components.

Since the advantages of these two approaches are complementary, the problem can be divided into two steps. First, the curved fatigue crack path and its SIF are calculated under constant amplitude (CA) loading in a specialized FE program, using small crack increments and automatic remeshing. Numerical methods are used to calculate the crack propagation path, based on the computation of the crack incremental direction, and the associated SIF  $K_I(\mathbf{a})$  and  $K_{II}(\mathbf{a})$ , where  $\mathbf{a}$  is the length along the crack path. The  $K_I(\mathbf{a})$  values are then used as an input to a fatigue program based on the local approach, where the actual VA loading is efficiently treated by the integration of the crack propagation equation, considering overload-induced retardation effects if required [1].

In this work, fatigue crack growth experiments under VA loading are performed on compact tension C(T) specimens made of cold-rolled SAE 1020 steel, modified with holes positioned to attract or to deflect the fatigue cracks. The curved crack paths are FE-predicted under CA loading, resulting in good estimates of the measured paths under VA loading. The results suggest that overloads do not deviate significantly the crack path predicted under constant amplitude loading, provided that the overload does not induce crack bifurcation or plastic zones with sizes comparable to the residual ligament. Experiments under VA loading are also performed on C(T) specimens without holes. Several crack retardation models are calibrated based on straight-crack data. These models are then used to successfully predict the curved crack growth behavior under VA loading of the hole-modified specimens.

## MIXED-MODE CRACK GROWTH CALCULATIONS

In FE mixed-mode crack growth calculations, three methods are generally used to compute the stress intensity factors along the (generally curved) crack path: the displacement correlation technique [2], the potential energy release rate computed by means of a modified crack-closure integral technique [3-4], and the J-integral computed by means of the equivalent domain integral (EDI) together with a mode decomposition scheme [5-6]. The EDI method replaces the J-integral along a contour by another one over a finite size domain, using the divergence theorem, which is more convenient for FE analysis.

Since Bittencourt et al. [7] showed that for sufficiently refined FE meshes all three methods predict essentially the same results, only the EDI method is considered in the calculations presented here. However, the other two methods also provide good results even for relatively coarse meshes.

The calculated Modes I and II SIF  $K_I$  and  $K_{II}$  are then used to obtain an equivalent SIF  $K_{eq}$ . The fatigue crack growth rate can then be computed from the equivalent stress intensity range  $\Delta K_{eq}$  by a simple McEvily-type model [8]:

$$\frac{da}{dN} = A \cdot (\Delta K_{eq} - \Delta K_{th})^m \quad (1)$$

where  $\Delta K_{th}$  is the threshold SIF and  $A$  and  $m$  are the conventional tensile crack growth rate parameters for the given material. An alternative Elber-type equation can be used based on the maximum equivalent stress intensity  $K_{eq}$  and on the crack opening value  $K_{op}$ , namely

$$\frac{da}{dN} = A \cdot (K_{eq} - K_{op})^m \quad (2)$$

Several models have been proposed to obtain  $K_{eq}$  from  $K_I$  and  $K_{II}$  (and  $K_{III}$ , when it is important). E.g., Tanaka [9] obtained an equivalent stress intensity model based on the displacements behind the crack tip reaching a critical value, leading to

$$K_{eq} = \left[ K_I^4 + 8 \cdot K_{II}^4 + \frac{8 \cdot K_{III}^4}{1-\nu} \right]^{1/4} \quad (3)$$

where  $\nu$  is Poisson's coefficient.

Another expression for  $K_{eq}$  can be derived for elastic loading under plane stress conditions, based on the relations between the potential energy release rate  $\mathcal{G}$  and the SIF [10], leading to

$$K_{eq} = \sqrt{K_I^2 + K_{II}^2 + (1+\nu) \cdot K_{III}^2} \quad (4)$$

Hussain et al. [11] used complex variable mapping functions to obtain  $\mathcal{G}$  at a direction  $\theta$  with respect to the crack propagation plane under Mode I and II combined loading. They assumed that crack extension occurs in a direction  $\theta = \theta_0$  that maximizes  $\mathcal{G}$ , leading to the maximum fracturing energy release rate ( $\mathcal{G}_{max}$ ) criterion. Thus, an equivalent SIF is obtained at  $\theta = \theta_0$  that maximizes the expression

$$K_{eq} = \sqrt{\frac{4}{(3+\cos^2 \theta)^2} \left( \frac{1-\theta/\pi}{1+\theta/\pi} \right)^{\theta/\pi} [(1+3\cos^2 \theta)K_I^2 - 8\sin \theta \cos \theta \cdot K_I K_{II} + (9-5\cos^2 \theta)K_{II}^2]} \quad (5)$$

The computed  $\theta_0$  values at each calculation step are used to obtain the crack incremental growth direction - and thus the fatigue crack path - in the linear-elastic regime.

Sih [12] proposed a criterion for mixed-mode loading based on the strain energy density  $S$  around the crack tip. It is assumed that the crack propagates in a direction  $\theta = \theta_0'$  that minimizes  $S$ . The associated equivalent SIF is then calculated at  $\theta = \theta_0'$  that minimizes the expression

$$K_{eq}^2 = \frac{1}{4(1-2\nu)} \{ (3-4\nu-\cos \theta)(1+\cos \theta) \cdot K_I^2 + 2\sin \theta \cdot [\cos \theta - 1 + 2\nu] \cdot K_I K_{II} + \\ + [4(1-\nu)(1-\cos \theta) + (1+\cos \theta)(3\cos \theta - 1)] \cdot K_{II}^2 + 4K_{III}^2 \} \quad (6)$$

Erdogan and Sih [13] proposed the maximum circumferential stress ( $\sigma_{\theta max}$ ) criterion, which considers that crack growth should occur in the direction that maximizes the circumferential stress in the region close to the crack tip. They considered the stresses at the crack tip under combined Mode I and II loading, given by summing up the stress fields generated by each mode:

$$\sigma_r = \frac{1}{\sqrt{2\pi r}} \left\{ \frac{1}{4} \left( 5\cos \frac{\theta}{2} - \cos \frac{3\theta}{2} \right) \cdot K_I - \frac{1}{4} \left( 5\sin \frac{\theta}{2} - 3\sin \frac{3\theta}{2} \right) \cdot K_{II} \right\} \quad (7)$$

$$\sigma_\theta = \frac{1}{\sqrt{2\pi r}} \left\{ \frac{1}{4} \left( 3\cos \frac{\theta}{2} + \cos \frac{3\theta}{2} \right) \cdot K_I - \frac{3}{4} \left( \sin \frac{\theta}{2} + \sin \frac{3\theta}{2} \right) \cdot K_{II} \right\} \quad (8)$$

$$\tau_{r\theta} = \frac{1}{\sqrt{2\pi r}} \left\{ \frac{1}{4} \left( \sin \frac{\theta}{2} + \sin \frac{3\theta}{2} \right) \cdot K_I + \frac{1}{4} \left( \cos \frac{\theta}{2} + 3\cos \frac{3\theta}{2} \right) \cdot K_{II} \right\} = -\frac{2}{3} \frac{\partial \sigma_\theta}{\partial \theta} \quad (9)$$


where  $\sigma_r$  is the normal stress component in the radial direction,  $\sigma_\theta$  is the normal stress component in the tangential direction and  $\tau_{r\theta}$  is the shear stress component. These expressions are valid both for plane stress and plane strain. The Maximum Circumferential Stress criterion assumes that crack growth begins on a plane perpendicular to the direction in which  $\sigma_\theta$  is maximum. The maximum value of  $\sigma_\theta$  is obtained when  $\partial \sigma_\theta / \partial \theta$  is zero, which is equivalent to equating  $\tau_{r\theta} = 0$ , according to Equation (9). The equation  $\tau_{r\theta} = 0$  has a trivial solution  $\theta = \pm \pi$  (for  $\cos(\theta/2) = 0$ ), and a non-trivial solution  $\theta = \theta_0''$  given by

$$\theta_0'' = 2 \arctan \left( \frac{1}{4} \frac{K_I}{K_{II}} \pm \frac{1}{4} \sqrt{\left( \frac{K_I}{K_{II}} \right)^2 + 8} \right) \quad (10)$$


where the sign of  $\theta_0''$  is the opposite of the sign of  $K_{II}$ . According to the  $\sigma_{\theta_{max}}$  criterion, the equivalent SIF is calculated at the value  $\theta = \theta_0''$ , which maximizes the expression

$$K_{eq} = \frac{1}{4} \left( 3 \cos \frac{\theta}{2} + \cos \frac{3\theta}{2} \right) \cdot K_I - \frac{3}{4} \left( \sin \frac{\theta}{2} + \sin \frac{3\theta}{2} \right) \cdot K_{II} \quad (11)$$

Several other criteria have been proposed in the literature, such as the ones by Nuismer, Amestoy et al., Richard, Schöllmann et al., and Pook [14]. A few of these criteria even predict the warping angle of a 3-D crack subject to Mode III loading. A comprehensive review of the proposed equivalent SIF and propagation angle expressions can be found in [14].



**Figure 1:** Crack propagation direction  $\theta$  as a function of the  $K_{II}/K_I$  ratio according to the  $\sigma_{\theta_{max}}$ ,  $G_{max}$  and  $S_{min}$  models.



**Figure 2:** Equivalent SIF  $K_{eq}$  as a function of the  $K_{II}/K_I$  ratio according to several models.

All presented models have notable differences if the amount of Mode II loading is significant. For instance, under pure Mode II loading, the propagation angle  $\theta$  is  $\pm 70.5^\circ$ ,  $\pm 75^\circ$  and  $\pm 82^\circ$  according to the  $\sigma_{\theta_{max}}$ ,  $G_{max}$

and  $S_{min}$  models, respectively, leading to  $K_{eq}$  values of approximately  $1.15 \cdot K_{II}$ ,  $1.60 \cdot K_{II}$  and  $1.05 \cdot K_{II}$  (assuming  $\nu = 0.3$ ). In addition, Tanaka's model results in this case in  $K_{eq} = 1.68 \cdot K_{II}$ , while Equation (4) furnishes  $K_{eq} = K_{II}$ . The values of  $\theta$  and  $K_{eq}$  obtained from each model are plotted in Figs. 1 and 2 as a function of the  $K_{II}/K_I$  ratio.

The differences among the studied models might be significant for mixed-mode fracture predictions, however they turn out to be negligible for fatigue crack propagation calculations. In fact, since all above models predict crack path deviation ( $\theta \neq 0$ ) under any  $K_{II}$  different than zero (see Fig. 2), they imply that fatigue cracks will always attempt to propagate in pure Mode I, minimizing the amount of Mode II loading, curving their paths if necessary to avoid rubbing their faces. As soon as the crack path is curved to follow pure Mode I, all models agree that  $K_{eq}$  is equal to  $K_I$ . Therefore, not only the crack path but also the associated SIF values calculated by any of the above criteria are essentially the same. This has been verified by Bittencourt et al. [7], who concluded from FE simulations that these criteria provide basically the same numerical results. Since the Maximum Circumferential Stress criterion is the simplest, even presenting a closed form solution, it is the one adopted in the present work.

## NUMERICAL PROCEDURE

Two complementary pieces of software, named **Quebra2D** and **VIDA** [1, 15, 16], have been developed to implement the two steps of this hybrid methodology. A brief description of both programs is presented below.

**Quebra2D** is an interactive graphical program for simulating two-dimensional fracture processes based on a FE self-adaptive mesh-generation strategy [15, 17]. This program includes all methods described above to compute the crack increment direction and the associated stress-intensity factors along the crack path. Moreover, its adaptive FE analyses are coupled with modern and very efficient automatic remeshing schemes, which substantially decrease the computational effort.


The automatic calculation procedure in **Quebra2D** is performed in 4 steps: (i) the FE model of the cracked structure is solved to obtain  $K_I$  and  $K_{II}$  and to calculate the corresponding crack propagation direction; (ii) the crack is increased in the growth direction by a (small) required step; (iii) the model is remeshed to account for the new crack size; and (iv) the process is iterated until rupture or until a specified crack size is reached. As a result, a list of  $K_I$  and  $K_{II}$  values is generated at short but discrete intervals along the predicted crack paths.

The second program, named **VIDA**, is a general-purpose fatigue design program developed to predict both initiation and propagation fatigue lives under VA loading by all classical design methods, including the **SN**, the **IIW** (for welded structures) and the **eN** for crack initiation, and the **da/dN** for crack propagation. It includes several load interaction models to predict overload and underload-induced crack retardation and acceleration. The program includes comprehensive database with mechanical properties of more than 13000 materials, hundreds of editable  $K_I$  and  $K_{II}$  SIF expressions and **da/dN** curves to be used in the calculations. In particular, **VIDA** accepts any crack growth equation and any SIF expression, making it an ideal companion to **Quebra2D**, which can be used to generate the required  $\Delta K$  expression if not available in its database.

## EXPERIMENTAL RESULTS

The FCG experiments were performed on cold-rolled SAE 1020 steel with yield strength **285MPa**, ultimate strength **491MPa**, Young modulus **205GPa**, and reduction in area **54%**, measured according to the ASTM E 8M-99 standard, with the analyzed weight percent composition: C 0.19, Mn 0.46, Si 0.14, Cu 0.11, Ni 0.052, Cr 0.045, Mo 0.007, Nb 0.002, Ti 0.002, Fe balance. The tests were performed at two **R = K<sub>min</sub>/K<sub>max</sub>** ratios, **R = 0.1** and **R = 0.7**, in a 250kN computer-controlled servo-hydraulic testing machine. The crack length was measured following ASTM E 647-99 procedures. The measured growth rates on 16 standard compact


tension C(T) test specimens were fitted by a modified McEvily  $da/dN$  equation (in m/cycle), as shown in Figure 3, where the propagation threshold under  $R = 0$  is  $\Delta K_0 = 11.5 \text{ MPa}\sqrt{\text{m}}$ , and the fracture toughness is  $K_C = 280 \text{ MPa}\sqrt{\text{m}}$ .



**Figure 3:** Modified McEvily  $da/dN$  equation fitted to the SAE 1020 steel data.


Three modified C(T) specimens were designed and tested, with width  $w = 29.5 \text{ mm}$  and thickness  $t = 8 \text{ mm}$ . Each one had a 7mm-diameter hole positioned at a slightly different horizontal distance  $A$  and vertical distance  $B$  from the notch root, as shown in Figure 4(a). Two very different crack growth behaviors had been predicted by the FE modeling of the C(T) specimens, depending on the hole position. The predictions indicated that the fatigue crack was always attracted by the hole, but it could either curve its path and grow toward the hole (“sink in the hole” behavior) or just be deflected by the hole and continue to propagate after missing it (“miss the hole” behavior).

Using the **Quebra2D** program, the transition point between the “sink in the hole” and the “miss the hole” crack growth behaviors was identified. The three modified C(T) specimens were designed so that specimens named CT1(CA) and CT1(VA) had the hole just half a millimeter above the transition point, and a specimen named CT2(CA) had the hole half a millimeter below it. The chosen specimen geometries were machined, measured, and FE remodeled, to account for small deviations in the machining process (Figure 5). In this way, it could be assured that the numerical models used in the predictions reproduced the real geometry of the tested specimens.




**Figure 4:** Measured dimensions of the hole-modified C(T) specimens (mm).

Specimens CT1(CA) and CT2(CA) were tested under CA loading, under a quasi-constant stress-intensity range  $\Delta K_I \approx 20 \text{ MPa}\sqrt{\text{m}}$  and load ratio  $R = 0.1$ .




**Figure 5:** Automatically generated FE mesh of the CT1(CA) and CT2(CA) specimens.

Two specimens were tested under VA loading: one standard C(T) specimen, and the holed CT1(VA). The VA load histories applied to the specimens are shown in Figure 6.



**Figure 6:** Applied load history (in kN) for standard C(T) and modified CT1(VA).


Figure 7 shows the predicted and measured crack paths for the three modified specimens (in mm) under CA or VA loading, presenting a very good match. This suggests that the curved crack paths predicted under CA loading give good estimates of the measured paths under VA loading. Therefore, assuming that the Linear Elastic Fracture Mechanics (LEFM) conditions apply, the discussed two-step methodology can be generalized to the VA loading case.




**Figure 7:** Predicted and measured crack paths for the modified C(T) specimens (mm).

The SIF values calculated under CA loading along the crack path using the **Quebra2D** program were exported to the **VIDA** software to predict fatigue life, considering load interaction effects. Figure 8 shows predicted and measured crack sizes for the modified C(T) specimens under CA loading.

Several crack retardation models were calibrated based on the standard C(T) data under VA loading, including the Constant Closure model [11] (where the crack opening load  $K_{op}$  was calibrated as 26% of the maximum overload SIF,  $K_{ol,max}$ ), a modified Wheeler model [18-19] (where the model's exponent was estimated as 0.51), and Newman's closure model [20] (generalized for the VA loading case, where the stress-state constraint factor was fitted as  $\alpha = 1.07$ , suggesting dominant plane-stress FCG conditions). The fitted load interaction parameters were then used to predict in the **VIDA** program the crack growth behavior under VA loading of the hole-modified CT1(VA) specimen, see Fig. 9. The significant retardation effects of the CT1(VA) specimen were very well predicted using these three load interaction models.




**Figure 8:** Predicted and measured FCG for modified C(T) specimens under CA loading.




**Figure 9:** Crack growth predictions (based on straight-crack calibrations) on a modified C(T) specimen under VA loading.

Finally, a larger modified C(T) specimen named CT2(VA) has been designed and tested under VA loading, with sizes shown in Figure 2(b). The applied VA load history is shown in Fig. 10. As seen in Fig. 11(a), in the beginning there is a good match between the predicted and measured crack paths. However, after an overload at about 750,000 load cycles in the history, there is a significant deviation in the crack path. After carefully examining the specimen surface, it was found that the crack tip had unexpectedly bifurcated due to the overload, see Fig. 11(b). Even though such crack bifurcations can be easily modeled using the **Quebra2D** program [21-22], it is very difficult to predict whether and when they are induced. In addition, this overload generated a very large plastic zone ahead of the bifurcated crack tip, with dimensions comparable to the length of the residual ligament between the crack and the hole, invalidating LEFM assumptions. Therefore, elastic-plastic FE calculations considering bifurcation effects would be required to predict the crack path of this specimen.





**Figure 10:** Applied load history for standard modified CT2(VA) specimens.



**Figure 11:** Predicted and measured crack paths for the CT2(VA) specimens.

## CONCLUSION

A two-phase methodology was presented to predict fatigue crack propagation in generic 2D structures. First, self-adaptive finite elements were used to calculate the fatigue crack path and the stress-intensity factors along the crack length  $K_I(a)$  and  $K_{II}(a)$ , at each propagation step. The computed  $K_I(a)$  was then used to calculate the propagation fatigue life by the local approach, considering overload-induced crack retardation effects.

Two complementary software have been developed to implement this methodology. The first is an interactive graphical program for simulating two-dimensional fracture processes based on a finite-element adaptive mesh-generation strategy. The second is a general-purpose fatigue design software developed to predict both initiation and propagation fatigue lives under variable loading by all classical design methods. Particularly, its crack propagation module accepts any stress-intensity factor expression, including the ones generated by the finite-element software.

Experimental results validated the proposed methodology, in particular suggesting that overloads do not significantly deviate the crack path predicted under simple loading. Moreover, the developed software demonstrated that effective and economical predictions of crack propagation paths and fatigue lives can be obtained for arbitrary two-dimensional structural components under variable amplitude loading, provided that they did not induce crack bifurcation or plastic zones with sizes comparable to the residual ligament.

## REFERENCES

1. Miranda, A.C.O., Meggiolaro, M.A., Castro, J.T.P., Martha, L.F., Bittencourt, T.N., *Fatigue Crack Propagation under Complex Loading in Arbitrary 2D Geometries*. ASTM STP 1411(4), 2002:120-145.
2. Shih CF, de Lorenzi HG, German MD. *Crack Extension Modeling with Singular Quadratic Isoparametric Elements*. Int Journal of Fracture, 1976;12:647-51.
3. Raju IS. *Calculation of Strain-Energy Release Rates with Higher Order and Singular Finite Elements*. Engineering Fracture Mechanics, 1987;28:251-74.
4. Rybicki EF, Kanninen MF. *A Finite Element Calculation of Stress-Intensity Factors by a Modified Crack Closure Integral*. Eng Fracture Mechanics, 1977;9:931-38.
5. Dodds RH Jr, Vargas PM. *Numerical Evaluation of Domain and Contour Integrals for Nonlinear Fracture Mechanics*. Report, Dept. of Civil Engineering, Univ. of Illinois, Urbana-Champaign, 1988.
6. Nikishkov GP, Atluri SN. *Calculation of Fracture Mechanics Parameters for an Arbitrary Three-Dimensional Crack by the Equivalent Domain Integral Method*. International Journal for Numerical Methods in Engineering, 1987;24:1801-21.
7. Bittencourt TN, Wawrzynek PA, Ingraffea AR, Sousa JLA. *Quasi-Automatic Simulation of Crack Propagation for 2D LEFM Problems*. Eng Fracture Mechanics, 1996;55:321-34.
8. McEvily AJ. Current Aspects of Fatigue. Metal Science, 1977;11:274-84.
9. Tanaka K. *Fatigue Propagation from a Crack Inclined to the Cyclic Tensile Axis*. Eng Fracture Mechanics, 1974;6:493-507.
10. Irwin GR. *Analysis of Stresses and Strains Near the End of a Crack Transversing a Plate*. J. Applied Mechanics, 1957;24:361-70.
11. Hussain MA, Pu SU, Underwood J. *Strain Energy Release Rate for a Crack under Combined Mode I and II*. ASTM STP 560, 1974:2-28.
12. Sih GC. *Strain-Energy-Density Factor Applied to Mixed Mode Crack Problems*. Int Journal of Fracture Mechanics, 1974;10:305-21.
13. Erdogan F, Sih GC. *On the Crack Extension in Plates under Plane Loading and Transverse Shear*. Journal of Basic Engineering, 1963;85:519-27.
14. Richard HA. *Theoretical Crack Path Determination*. Int Conference on Fatigue Crack Paths, Parma, Italy, 2003.
15. Miranda, A.C.O., Meggiolaro, M.A., Castro, J.T.P., Martha, L.F., Bittencourt, T.N. *Fatigue Life and Crack Path Prediction in Generic 2D Structural Components*. Engineering Fracture Mechanics, 2003; 70:1259-1279.
16. Meggiolaro, M.A., Castro, J.T.P. *ViDa - a Visual Damagemeter to Automate the Fatigue Design under Complex Loading (in Portuguese)*. Journal of the Brazilian Society of Mechanical Sciences, 1998; 20:666-685.
17. Wawrzynek, P.A., Ingraffea, A.R. *Interactive Finite Element Analysis of Fracture Processes: An Integrated Approach*. Theor. Appl. Fract. Mech., 1987; 8:137-50.
18. Wheeler, O.E. (1972) *Spectrum Loading and Crack Growth*. J. Basic Eng.: 181-186.
19. Meggiolaro, M.A., Castro, J.T.P. *An Evaluation of Elber-Type Crack Retardation Models*. SAE #2001-01-4063, SAE 2001:207-216.
20. Newman, J.C. Jr. *A Crack Opening Stress Equation for Fatigue Crack Growth*. Int Journal of Fracture, 1984; 24(3):R131-R135.
21. Meggiolaro, M.A., Miranda, A.C.O., Castro, J.T.P., Martha, L.F. *Stress Intensity Factor Equations for Branched Crack Growth*. Engineering Fracture Mechanics, vol. 72, n. 17, pp. 2647-2671, 2005.
22. Meggiolaro, M.A., Miranda, A.C.O., Castro, J.T.P., Martha, L.F. *Crack Retardation Equations for the Propagation of Branched Fatigue Cracks*, International Journal of Fatigue, vol 27, n. 10-12, pp. 1398-1407, 2005.